

## VERNICE ZINCANTE

### Zinc spray paint

### Technical specifications

**VERNICE ZINCANTE** is a paint used as a primer and finishing coat to protect materials and equipment exposed to severe corrosion conditions. The product can be overpainted with any synthetic or acrylic enamel.

### Instructions for use

Clean the surface to be painted from grease, dust, and rust.

Turn the can upside down and shake vigorously for about one minute.

Spray from a distance of 20-30 cm with slow, steady horizontal movements; after about one minute, spray vertically.

### Application

Apply **VERNICE ZINCANTE** as supplied.

### Consumption

The consumption of **VERNICE ZINCANTE** varies depending on the method of use and the required application.

### Warnings

Pressurized container.

Protect from sunlight and do not expose to temperatures above 50°C.

Do not pierce or burn, even after use.

Use and store in a ventilated, cool place.

Do not smoke during use.

Use the product following good work practices, avoiding environmental dispersion.

Wear appropriate protective equipment (gloves, safety glasses, etc.).

Store the product indoors in its original closed packaging, away from weather, frost, and heat sources.

Do not release into the environment; follow local regulations for disposal.

Always perform a preliminary test before use.

### Packaging

6-pack boxes, aluminum color

400mL

Barcode: 80-20709-001964

### CHEMICAL AND PHYSICAL PROPERTIES

Physical state	Pressurized liquid
Color	Grey, White
Smell	Characteristic, solvent-like
Flash Point	-104°C (referring to the propane content)
Density (T=20°C)	0,75-0,80 Kg/L
Water solubility	Insoluble
Pressure (T=20°C)	3,0±0,5 Bar
Pressure (T=50°C)	7,0±0,5 Bar
VOC content	256g (per 400mL can)

Technical Data Sheet code: 4330-Revision 01 of 01/10/2025

Via G. Galilei 39 • 35035 Mestrino (PD) • tel +39 049 904 8611 • fax +39 049 900 1695

[www.multichimica.it](http://www.multichimica.it) • [mailbox@multichimica.it](mailto:mailbox@multichimica.it)



The information is, to the best of our knowledge, accurate and correct, but any indication and/or suggestion provided is given without guarantee, as the conditions of use are beyond our direct control. In case of uncertainty, preliminary testing is always recommended.