

CODE	Art. 3456
TRADE NAME	CEMENTO REFRATTARIO
PRODUCT TYPE	REFRACTOR CEMENT

Technical characteristics

The product is used for repairs of chimneys, walls, boilers: therefor ideal for high temperatures.

Applications

Dissolve the product with 20% water until a homogeneous paste is obtained; to obtain a larger grip, add 325 normal cement to 1/1 with refractory cement; then wet abundantly the parts to be treated. Maximum thickness 4 cm. Wait 30 minutes for a good grip, hardens in 6 hours.

Important

It is advisable to prepare small quantities of material, since the mixture hardening is no longer usable. Store the product in a cool, dry place, in the original original packaging. Wash the equipment used with water before the solidification of the product. Dispose of residues of material in accordance with the regulations in force at the place of use. The product is not considered to be a dangerous substance; Avoid contact with eyes and skin, however. In case of contact, wash with plenty of water. Always perform a preliminary test before using. Use in accordance with good working practices, however, avoid dispersing the product or packaging in the environment.

Chemical and Physical Property	
Physical state	Solid
Melting point	1300 °C
Solubility	None

QUALITY CONTROL MANAGER

COMMERCIAL
MANAGER

VALIDITY FROM

05.09.2016

via G. Galilei 39 • 35035 Mestrino (PD) • tel +39 049 904 8611 • fax +39 049 900 1695

www.multichimica.it • clienti@multichimica.it • lab@multichimica.it

Multichimica S.p.A. non si assume nessuna responsabilità derivante dall'uso del prodotto, che deve comunque essere sempre conforme alle informazioni tecniche fornite. Multichimica S.p.A. assicura da parte sua che il prodotto è conforme alle specifiche tecniche.

Multichimica S.p.A. does not take upon itself any responsibility originated by product use. The product must be always in conformity with technical information. Multichimica S.p.A. assures product conformity.

